

---

## Material Specification 532—Supplementary Cementitious Materials

### 1. Scope

This specification covers the quality of supplementary cementitious materials for concrete.

### 2. Quality

Fly ash used as a partial substitution of Portland cement shall conform to the requirements of ASTM C 618, Class C or F except the loss on ignition shall not exceed 3 percent, unless otherwise specified. Lot-to-lot variation in the loss on ignition shall not exceed 1 percent. When specified, fly ash shall conform to one or more of the supplementary optional physical requirements listed in ASTM C618.

Blast-furnace slag used as a partial substitution of portland cement shall conform to ASTM Standard C 989 for ground granulated blast-furnace slag.

